

- DESCRIPTION :** A lightfast, aqueous, polyurethane dispersion polymer designed to produce unequalled clarity and gloss.
- SUGGESTED USES:** **HD-2209** was designed for wood finishing applications but can be used on a wide variety of both rigid and flexible substrates. Use wherever gloss and clarity are of paramount importance.
- CHARACTERISTICS:** Wet look gloss
Glass-like clarity
Mirror like definition-of-image
Adhesion to a wide variety of substrates; wood, plastics, textile etc.
Dilution and clean up with ordinary tap water
- APPLICATION:** **HD-2209** is used as supplied by spray, dip, and rotogravure techniques. It can be thickened for knife-over roll or similar methods
- DRYING:** Can be air dried at ambient conditions, if desired. Forced air drying in conventional ovens will minimize drying time.

<u>PHYSICAL PROPERTIES</u>		<u>TENSILE PROPERTIES</u>	
SOLIDS:	35.0%(+/- 1%)	(Tested at 20 inches/minute)	
VISCOSITY:	50-150 cps	ELONGATION:	330%
PH:	7.5-10	ULT. TENS. STR.	7300 PSI
DENSITY:	8.8 lb/gal	100% MODULUS:	3500 PSI
SOFTENING POINT:	330F	200% MODULUS:	5000 PSI
V.O.C. CONTENT:	1.10 lbs/gal	300% MODULUS:	6700 PSI

***PLEASE CONTACT US FOR SPECIFIC RECOMMENDATIONS ON THICKENERS OR CROSSLINKERS**

SPECIAL NOTE: Mix well before removing product from containers. Container lids must be re-sealed tightly with the plastic header film after each use.

STORAGE STABILITY: The product must be stored in a controlled environment between 5 – 40°C and protected from direct exposure to sunlight. Shelf-life is 1 year from manufacture date (see lot # for date).

This information is believed to be accurate but is not guaranteed and we assume no legal responsibility for its accuracy. User should test the product to determine its suitability for their particular purpose. Nothing presented here is to be construed as a recommendation or inducement to use our product. We shall not be liable for any claims for damages, whether based on contract, negligence, and strict liability in tort or otherwise. Our products are sold without any implied warranty of merchantability or fitness for a particular purpose.

东莞市赢懋贸易有限公司

地址: 东莞市南城区鸿福路中环财富广场

E-mail 地址: euroland@euroland.net.tw

电话 0769-2288 9931 传真 0769-2288 8557