Hauthaway

L-3155 Established 1852

DESCRIPTION: A self-crosslinking, aliphatic, water-based polyurethane dispersion

designed for use in high performance concrete and wood floor coatings.

SUGGESTED USES: L-3155 employs a unique air-dry, self-crosslinking mechanism to impart

chemical-resistance, abrasion-resistance and mar-resistance properties which equal or exceed those of two-component, water-based floor coating

systems currently used in the market.

CHARACTERISTICS: < One-component, self-crosslinking polymer

< High level of toughness, abrasion- and mar-resistance

Outstanding water and chemical resistanceExcellent exterior weathering performance

APPLICATION: L-3155 can be used as a sole vehicle or blended with acrylic emulsions for

spray or rotogravure applications. Rheology modifications can be made

with associative thickeners for alternative application methods.

DRYING: Ambient drying temperatures between $60 - 90^{\circ}$ F are ideal to produce

coatings with optimal film properties. Allow 5 - 7 days to attain full cure

properties.

PHYSICAL PROPERTIES*

TENSILE PROPERTIES**

| SOLIDS | 32% (± 1%) | (TESTED AT 20 INCHES/MINUTE) | |
|-----------------|----------------------|------------------------------|----------|
| VISCOSITY | 50-300 cps | ELONGATION | 160 % |
| pН | 7.0-10.0 | TENSILESTRENGTH | 2400 psi |
| DENSITY | 8.8 lbs/gal | 100% MODULUS | 1850 psi |
| SOFTENING POINT | NA°F | 200% MODULUS | NA |
| VOC CONTENT | 246 g/l (less water) | 300% MODULUS | NA |

^{*}Provisional – Physical properties are considered provisional until at least 10 production batches have been produced.

SPECIAL NOTE: Mix well before removing product from containers. Container lids must be re-sealed tightly with the plastic header film after each use.

STORAGE STABILITY: The product must be stored in a controlled environment between 5 – 40°C and protected from direct exposure to sunlight. Shelf-life is 1 year from manufacture date (see lot # for date).

This information is believed to be accurate but is not guaranteed and we assume no legal responsibility for its accuracy. User should test the product to determine its suitability for their particular purpose. Nothing presented here is to be construed as a recommendation or inducement to use our product. We shall not be liable for any claims for damages, whether based on contract, negligence, and strict liability in tort or otherwise. Our products are sold without any implied warranty of merchantability or fitness for a particular purpose.

东莞市赢懋贸易有限公司

地址: 东莞市南城区鸿福路中环财富广场 E-mail 地址: euroland@euroland.net.tw 电话 0769-2288 9931 传真 0769-2288 8557

^{**}Films are coalesced with 5% DPM to ensure optimal film formation.