

- DESCRIPTION:** Co-solvent-free, hard, fire retardant, aliphatic, water-borne urethane dispersion.
- SUGGESTED USES:** **HD-2334** was designed for use as a coating or finish for synthetic textile fabrics that must have permanent fire retardancy. This unique urethane dispersion is manufactured at high solids and without the use of solvent. Low add-on levels of **HD-2334** will enable synthetic fabrics to pass various FR tests including NFPA-701, MVSS-302, & others. **HD-2334** is well suited for use in textile coatings, such as automotive upholstery, that require outstanding strength and fire retardancy without the use of antimony-oxide/decabrome chemistry. The high solids and solvent-free nature of **HD-2334** make it a very cost effective urethane.
- CHARACTERISTICS:** Co-solvent-free and high solids.
Permanent, non-leaching fire retardancy.
Excellent cost/performance ratio.
Hard, tough, flexible, dry film.
Excellent UV Resistance.
Excellent low temperature flex crack resistance.
Very good abrasion resistance.
- APPLICATION:** **HD-2334** may be sprayed or pad bathed as supplied. It may be thickened for knife-over-roll or similar methods.
- CURING:** This product displays excellent strength properties as supplied, although melamine-formaldehyde (3-6 phr) may be added to enhance performance.

<u>PHYSICAL PROPERTIES</u>		<u>TENSILE PROPERTIES</u>
SOLIDS:	45.0%(+/- 1%)	(Tested at 20 inches/minute)
VISCOSITY:	50-500 cps	ELONGATION: 200%
PH:	6.5-9.5	ULT. TENS. STR. 3500 PSI
DENSITY:	8.9 lb/gal	100% MODULUS: 2500 PSI
MELT POINT:	350 F	200% MODULUS: 3500 PSI
V.O.C. CONTENT:	<0.1%	300% MODULUS: NA

SPECIAL NOTE: Mix well before removing product from containers. Container lids must be re-sealed tightly with the plastic header film after each use.

STORAGE STABILITY: The product must be stored in a controlled environment between 5 – 40°C and protected from direct exposure to sunlight. Shelf-life is 1 year from manufacture date (see lot # for date).

This information is believed to be accurate but is not guaranteed and we assume no legal responsibility for its accuracy. User should test the product to determine its suitability for their particular purpose. Nothing presented here is to be construed as a recommendation or inducement to use our product. We shall not be liable for any claims for damages, whether based on contract, negligence, and strict liability in tort or otherwise. Our products are sold without any implied warranty of merchantability or fitness for a particular purpose.

东莞市赢懋贸易有限公司

地址: 东莞市南城区鸿福路中环财富广场

E-mail 地址: euroland@euroland.net.tw

电话 0769-2288 9931 传真 0769-2288 8557